

BiBaBerry Lipstick – “Number One”

Color Cosmetics

Ref: CC/2183/EU

Product Name	INCI Name	%W/W	Supplier
A			
		100.00	
Belsil PDM 20	Trimethylsiloxyphenyl Dimethicone	14.80	www.wacker.com
Kahlwax 2442	Copernicia Cerifera Cera	2.50	www.kahlwax.com
Kahlwax 2039	Candelilla Cera	4.00	www.kahlwax.com
Kahlwax 8139	Cera Alba	3.50	www.kahlwax.com
Kahlwax 1899	Ozokerite	4.00	www.kahlwax.com
Softisan 649	Bis-Diglyceryl Polyacyladipate-2	16.30	www.sasolwax.com
Lipocire A Pellets	C10-18 Triglycerides	3.00	www.gattefosse.com
Panale L14E	Hydrogenated Polyisobutene	14.00	www.ineos.com
Silshine 151	Phenylpropyldimethylsiloxyisilicate	5.00	www.momentive.com
Lexgard O	Caprylyl Glycol	1.00	www.inolex.com
dl-alpha-Tocopheryl Acetate	Tocopheryl Acetate	1.00	www.imcdgroup.com
B			
Belsil PDM 20	Trimethylsiloxyphenyl Dimethicone	10.00	www.wacker.com
GARAMITE-7308 XR	Quaternium-90 Sepiolite (and) Quaternium-90 Montmorillonite	1.50	www.eckart.net
C			
MIRAGE Glamour Red	Calcium Sodium Borosilicate (and) Titanium Dioxide (and) Tin Oxide	10.00	www.eckart.net
SYNCRYSTAL Blue	Synthetic Fluorphlogopite (and) Titanium Dioxide (and) Tin Oxide	5.00	www.eckart.net
Red 27 Lake (CI 45410) (20%)	Red 27 (and) Castor Oil	3.90	
Blue 1 (CI 42090) (33%)	Blue 1 (and) Castor Oil	0.10	
Cocos	Aroma	0.40	www.pura-natura.com

Procedure:

1. Melt phase A by heating to 80-85°C
2. Predisperse GARAMITE 7308 in Belsil PDM 20 and add to phase A
3. Add phase C and stir until uniform
4. Cool down to 75°C and pour into lip stick mold

- ⇒ It features a shimmery berry shade with a sparkling glow
- ⇒ GARAMITE-7308 XR promotes anti-settling and improves the spreadability

Stability:

Stable for at least 6 months at RT and 40°C.
Stable for at least 1 month at 50°C.

Customer Support

ECKART GmbH
info.eckart@altana.com

ECKART America Corporation
info.eckart.cosmetics@altana.com

ECKART Asia Limited
info.eckart.asia@altana.com

This document does not constitute a legally binding obligation of Eckart. While the information contained herein and our technical advice – whether verbal, in writing or by way of trials – are given in good faith, it is provided for your guidance only. We recommend testing our products as to their suitability for your envisaged purpose prior to use. Furthermore, you are responsible for observing all laws and regulations relevant to any products mentioned herein and the products' application. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties.

Date: 04.04.2023
Revision : 04.04.2023

